

DESCRIPTION

- ADEX MICATEX finish coat is a trowel-applied, factory-mixed architectural wall coating available in 12 standard colours as well as custom colours (upon request). Refer to the ADEX Texture Chart or www.adex.ca to view the wide variety of ADEX finish coats available.

USE

- MICATEX finish coat provides a textured, coloured surface for exterior or interior applications.

CHEMISTRY

- 100% acrylic polymer.

PIGMENTATION

- Coloured grains of silica and mica in a transparent acrylic binder.

PACKAGING

- 22.6 kg (50 lbs) plastic pail.

COVERAGE

- Approximately 8.4 m² to 10.2 m² (90 ft² to 110 ft²) per pail.
- Coverage is approximate and varies based on the substrate, job conditions and the individual application techniques.

SURFACE PREPARATION

- Surfaces must be clean, dry, and in good condition, without efflorescence, grease, oil, paint or other bond-inhibiting substances.
- Surface temperatures must not be below 5 °C (41 °F).
- An undercoat of ADEX PRIMEX coloured primer is mandatory with all MICATEX finishes. Consult an ADEX representative for the appropriate PRIMEX colour to be used.

MIXING

- Mix with a clean, rust-free electric drill and paddle mixer prior to use.
- A small quantity of clean, potable water may be added to the finish coat to adjust its viscosity.

APPLICATION

- Using a clean, stainless steel trowel, apply a small amount of MICATEX finish coat to a thickness slightly greater than the largest aggregate. Next, scrape the trowel back across the finish coat to create an even application the same thickness as the largest aggregate.
- After the finish coat has slightly dried, use a clean, wet stainless steel float, working in the same direction to achieve the desired final texture. Clean trowel regularly.
- On large wall surfaces, work in teams; one applying the finish coat and the other floating the final texture. Do not allow cold joints to occur in the middle of a wall. Make sure that the wall is separated in smaller areas.

Accelerated Weathering

ASTM D 822 (exposed 2,500 hours):

Pass.

Salt Spray Resistance

ASTM B 117 (exposed 300 hours):

Pass.

Freeze-Thaw Resistance

ASTM C-666, A (50 cycles):

No Deterioration.

Mildew Resistance

U.S. Military Standards 810E:

Pass.

Vapour Permeability

ASTM E96-95:

437 ng/Pa·s·m²

- Properties
- Test Method
- Result

CLEAN UP

- Immediately wash tools with water while material is still wet. Hardened material will have to be removed physically.

CURING

- Approximately 24 hours under normal climatic conditions.
- Curing time varies according to the ambient and surface temperature, and the relative humidity. Final curing is achieved after 2 weeks.

STORAGE

- Protect material from direct sunlight, extreme heat and freezing temperatures.
- Store unused material in a container with a tight-fitting lid.

SHELF LIFE

- Minimum 12 months if properly stored in an airtight container.

LIMITATIONS

- Ambient and surface temperatures must be at or above 5 °C (41 °F) for a minimum of 24 hours.
- During installation, minimise the containers' exposure to extreme heat (temperatures over 32 °C (90 °F)).

RESTRICTIONS

- ADEX MICATEX finish coat is not designed for applications over large surface areas. Control joints or natural breaks are required every 9 m² (100 ft²) (maximum spacing).
- ADEX finish coat must not be applied onto horizontal exterior surfaces or onto surfaces directly in contact with moisture over prolonged periods.
- The minimum slope of the surface must be 6:12.
- Do not apply finish coat into sealant joints or onto surfaces to which caulking will be installed.
- ADEX finish coat must be installed on a substrate that has been approved by ADEX Systems Inc.

MAINTENANCE

- Please refer to our MAINTENANCE GUIDE bulletin.

This document contains current information on the product. It is only provided as a guide and is subject to modifications at any time without notice. ADEX Systems Inc. reserves the right to make any modification according to technological progress. Specialised designers, architects, engineers or other professionals that choose to make any use of this information bear the complete responsibility, whatever it be, direct or indirect, that could follow from such use. ADEX Systems Inc. does not bear any responsibility that could give way to damages, defaults, defects, deficiencies, prejudices, loss or decrease of profit, be they direct or indirect, resulting from such use of this information by specialised designers, architects, engineers or other professionals. Please refer to www.adex.ca for the latest version of this document.

May 2010