



• QUALITY

• SERVICE

• INTEGRITY



Hamilton Drywall Products Pro-Tex

is a polystyrene-based aggregate ceiling texture. When sprayed it produces a white, medium texture finish. Pro-Tex mixes very easily without lumps; sprays and atomizes very easily, has good wet and dry hide and high coverage. Pro-Tex can be applied to a variety of properly prepared substrates including drywall, plaster and concrete.

Job Conditions:

Maintain a minimum air, surface and texture material temperature of 10° C (50° F) for 48 hours prior to application and until completely dry and stable.

Surface Preparation:

All surfaces must be firm, clean, dry and free of foreign substances.

The absorption rate of the surface that Pro-Tex is applied to may cause variation in the texture pattern.

NEW DRYWALL should be primed with one or more coats of Hamilton's Prep-Tex Plus prior to texture application. Paint must be completely dry prior to texture application.

CONCRETE surfaces must be aged at least 60 days prior to texture application. Particular caution should be exercised to determine the presence of efflorescence, dirt, dust, grease, separating and/or bond breaking agents, or a latent layer of cement. After removal of any of the foregoing, any irregularities in the concrete surface should be filled and smoothed with the appropriate Hamilton products.

Mixing:

In a clean container mix mechanically with approximately 14 liters of clean water per 15 kg bag. Slowly add powder to water and continue mixing until mixture is free of lumps. Re-mix after 10-15 minutes, adding more water as required. Use mixed material within 24 hours.

Application:

For interior use only. This product can be sprayed with a hand held hopper, stator tube or pressure pot machine.

Coverage/Yield:

Approximately 33-42 square meters (350-450 square feet) per 15 kg bag.
Approximate yield per 15 kg bag – 35 liters.

Storage/ Shelf Life:

Rotate inventory regularly and store in a dry and low humidity environment.



Submittal Approval
Stamp / Signature